

# PATENT ABSTRACTS OF JAPAN

(11)Publication number : 05-098421

(43)Date of publication of application : 20.04.1993

(51)Int.Cl.

C23C 14/06

C23C 14/30

G09F 9/30

(21)Application number : 03-259504

(71)Applicant : FUJI ELECTRIC CO LTD

(22)Date of filing : 08.10.1991


(72)Inventor : KATO HISATO  
KAWASHIMA TOMOYUKI  
TANIGUCHI HARUTAKA  
SHIBATA KAZUYOSHI

## (54) FORMATION OF ELECTROLUMINESCENCE LIGHT EMITTING FILM

### (57)Abstract:

**PURPOSE:** To improve the light emitting brightness of the light emitting film which consists of zinc sulfide as its base material and is used for an electroluminescence display panel, etc., by forming this film with good crystallinity.

**CONSTITUTION:** A vapor deposition source 20 for sintered pellets, etc., formed by previously adding a light emission center element to a base material is heated by a means, such as electron beam EB, etc., to evaporate the pellets and the light emitting film 4 is formed at 1 to 50 $\mu$ m/sec by a vacuum vapor deposition method, by which the crystal grain size of the base material in the light emitting element 4 is increased and the intrusion of abnormal particles by the bumping of the evaporating source 20 is lessened. The crystallinity of the light emitting film 4 is improved and the electroluminescence light emitting brightness is enhanced.



## LEGAL STATUS

[Date of request for examination] 23.07.1997

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration] withdrawal

[Date of final disposal for application] 07.02.2000

[Patent number]